



BEGOODTEX

TEST REPORT SUMMARY

This document contains selected pages from the original laboratory report for customer reference only.



COMPLETE REPORT AVAILABLE

For the full test report or additional certification documents, please contact BEGOODTEX.

CONTACT US



WEBSITE

www.begoodtex.com



EMAIL

suliya.sun@begoodtex.com



WHATSAPP

+86 15355543590



ONLINE CHAT

Available on our website



ABOUT BEGOODTEX

BEGOODTEX is a professional manufacturer specializing in inherently flame retardant textiles since 2013. Providing certified, reliable textile solutions for customers worldwide.

共 1 页 第 1 页

委托单位	绍兴市必固纺织品有限公司		检验类型	委托检验	来样日期	2015. 01. 16
生产单位	-----		委托人	-----	签发日期	2015. 01. 20
样品名称	面料		商标	-----	标称等级	合格品
样品信息	一种 米黄色针织物。					
声明款号	-----					
检验依据	GB/T 19817-2005《纺织品 装饰用织物》(悬挂类)合格品 GB 18401-2010《国家纺织产品基本安全技术规范》C类					
检验项目		单位	标准值	实测值	单项判定	检测方法标准
pH值		-----	4.0~9.0	6.3	符合	GB/T 7573-2009
甲醛含量		mg/kg	≤300	未检出	符合	GB/T 2912.1-2009
异味		-----	无	无	符合	GB 18401-2010 6.7
可分解致癌芳香胺染料(24种)		mg/kg	≤20	未检出	符合	GB/T 17592-2011 GB/T 23344-2009
耐水色牢度	变色	级	≥4	4-5	符合	GB/T 5713-2013
	沾色	级	≥3	4-5		
耐酸汗渍色牢度	变色	级	≥3	4-5	符合	GB/T 3922-2013
	沾色	级	≥3	4-5		
耐碱汗渍色牢度	变色	级	≥3	4-5	符合	GB/T 3922-2013
	沾色	级	≥3	4-5		
耐干摩擦色牢度	沾色	级	≥3-4	4-5	符合	GB/T 3920-2008
耐湿摩擦色牢度	沾色(浅)	级	≥3	4-5	符合	GB/T 3920-2008
耐光色牢度	变色	级	≥4	4-5	符合	GB/T 8427-2008 方法3
水洗尺寸变化率	直向	%	+2.0~-5.0	-1.0	符合	GB/T 8628-2013 GB/T 8629-2001(5A A) GB/T 8630-2013
	横向	%	+2.0~-5.0	-1.1		


pH值萃取介质为氯化钾溶液。

甲醛含量的检出限为20mg/kg, 低于检出限的结果报告为“未检出”。

可分解致癌芳香胺染料的检出限为5mg/kg, 低于检出限的结果报告为“未检出”。

样品粘贴处

以下空白



备注

相关报告编号(必要时填写):

检验人对来样负责, 复印件未重新加盖红色检验专用章无效。

批准

田媛

审核

朱永峰

编制

董泽军